

### Technical Data

Sign Series		510 gsm	
PROPERTIES	TEST METHOD	RESULT	UNIT
<b>Total Weight</b>	DIN EN ISO 2286-2	510	g/sq.m
		15.0	oz/sq.y
<b>Yarn (W/F)</b>	DIN EN ISO 2060	300 / 300	Denier
		330 / 330	Dtex
<b>Threads(W/F)</b>	DIN EN ISO 1409-2	42 / 40	Per inch
		17 / 16	Per cm
<b>Tensile Strength(W/F)</b>	DIN 53354	120 / 95	Kg/5cm
		1176 / 931	N /5cm
		134 / 106	lbs/inch
<b>Tear Resistance(W/F)</b>	DIN 53363	10 / 8	Kg
		98 / 78	N
		11 / 9	lbs
<b>Welding Adhesion</b>	DIN 53357	4.0	Kg/5cm
		39.2	N /5cm
		4.5	lbs/inch
<b>Temperature Resistance</b>	DIN 53361	-30 ~ +70 °C	
<b>Max Width</b>	DIN EN ISO 2286-1	3.2	Meter
		197.0	Inch
<b>Flame Retardant</b>	NFPA-701, DIN4102-B1,	Optional	
<b>Environmental</b>	EN-71, RoHs	Optional	

The information provided on this data sheet represents typical physical properties and does not constitute a specification. No liability will be accepted for errors and omissions and under no circumstances shall Flex-Europa be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet .All Flex-Europa vinyl's are sold subject to our Conditions of Sales.

Flex-Europa also retains the right to change sizes and specifications of products without prior notice.

Note: The modification of the data & contents above will not especially be notified